

**PROPERTIES OF ANTIFRICTIONAL AND IS ANTIFRICTION-WEAR PROOF  
COMPOSITE POLYPROPYLENE AND POLYETHYLENE MATERIALS****Soyibjon Negmatov**

<sup>1</sup> State Unitary Enterprise “Fan va tarakkiyot” at Tashkent state technical university named after Islom Karimov, Tashkent, Uzbekistan

**Abed Nodira**

<sup>1</sup> State Unitary Enterprise “Fan va tarakkiyot” at Tashkent state technical university named after Islom Karimov, Tashkent, Uzbekistan

**Tukhtasheva Malohat**

<sup>2</sup>Tashkent Institute of Chemical Technology, Tashkent, Uzbekistan

a) Corresponding author: [abed.n.s@inbox.ru](mailto:abed.n.s@inbox.ru)

b) [nafasovnanafasovna@gmail.com](mailto:nafasovnanafasovna@gmail.com)

**Abstract**

Are designed aitifriktsionno - wearproof polypropylene and polyethylene compositions of functional purpose for working bodies of the cotton cars and mechanisms providing functionally important physicommechanical, triboktekhnichesky and operational properties of the composite polymeric materials working in the conditions of interaction with cotton raw. They quite meet the functional requirements imposed to materials of details of the rubbing couples of working bodies of the cotton cars and mechanisms used on procuring points and the cotton-processing plants.

To use developed composite polymeric materials as materials for details of the rubbing couples of working bodies of cotton cars and mechanisms, in the conditions of frictional a between effect of with cotton - a raw leads to increase of productivity of cars for of 12-16% and a lower of power consumption for of 7-18%, damages of cotton fibers and broken up of seeds, and also eliminations of possible fire of a cotton-raw and education having reeled up fibers on surfaces of composite details.

**Keywords**

composition, polypropylene composition, polyethylene composition, composite polymeric material, ant frictional material, ant frictional and wear proof material, property, physic mechanical properties, tribotechnical properties, cotton raw.

When developing polymeric composite materials by the most important the choice of material and fillers is. This choice is carried out taking into account purpose of material: for anti-frictional material is a low coefficient of friction with cotton raw in various service conditions; for the wear proof – the minimum wear, and the low coefficient of friction and low wear ability of material at friction with cotton raw are necessary for ant frictional and wear proof composite material. The friction of cotton raw with composite material has the difficult nature. At friction influence the mechanism of interaction of these bodies both molecular, and mechanical process. Specifics of the contacting bodies are caused by emergence of electrostatic forces. Proceeding from it, it is established that the friction of cotton raw with composite material has molecular mechanical and the electric nature. These results allow is directed to change and regulate properties of materials, providing their compliance to requirements imposed to the composite polymeric materials working at interaction with cotton raw.

Thus, for creation of composite materials of anti-frictional appointment it is necessary to seek for increase of durability of material, decrease in temperature and reduction of size of a charge of static electricity in a friction zone. And when developing composite material of anti-frictional and wear proof (AW) appointment it is necessary to consider requirements of the minimum values of coefficient of friction and intensity of wear.

These tasks can be solved by different introduction of fillers, including systems of hybrid fillers. When developing composite materials as fillers graphite, soot, a kaolin, talc, fiber glass were used, wollastonit also cotton lint. However each of them has the shortcomings and advantages. By pilot studies it is established that fiber glass, wollastonit and cotton lint increase coefficient of friction and reduce intensity of wear. Graphite, soot, a kaolin and talc reduce friction coefficient, but increase wear ability of composite materials, and also improve warm and conductivity and, thereby, reduce temperature and size of a charge of static electricity, the contacting couples arising in a zone of friction. And, efficiency of these fillers, especially fibrous, is considerably shown at their smaller contents, that is at the smaller content of fiber glass intensity of wear considerably decreases, and at further increase in their contents intensity of wear of composite materials reduces a little decreases, but the friction coefficient sharply increases. The most effective decrease in coefficient of friction of composite materials with cotton raw is observed at introduction of soot and graphite.

**Table 1 Properties of antifrictional and is antifriction-wearproof composite polypropylene and polyethylene materials**

Indicators	Composite polymeric materials					
	APEC-1	APEC-2	AWPEC	APPC-1	APPC-2	AWPPC
Breaking point at a bend,MPa	40,3	42,6	49,0	105,0	115,2	112,5
Impact strength, kJ/m <sup>2</sup>	20,3	25,7	32,4	112,4	117,5	125,4
Hardness on Brinell, MPa	66,4	70,5	62,4	92,5	97,5	89,3
Elasticity module at a bend, GPa	0,75	0,78	0,90	1,81	2,05	2,0
Friction factor, f	0,27	0,28	0,31	0,25	0,26	0,28
Intensity of wear, I · 10 <sup>10</sup>	5,4	5,2	4,0	2,7	2,5	2,45
Temperature in friction zone, K	315	310	308	314	300	303
Value of charge of static electricity, Q · 10 <sup>-7</sup> , Kl	22,2	19,3	15,1	18,4	16,1	16,2

*The note: values I and f at P = 0,02 MPa, V = 2,0 km/s; AWCPM are obtained on the base of additives and polymer binders on thermal extruder mixer. R-specific pressure, V-speed of sliding, W-humidity of cotton raw.*

On the basis of the aforesaid, us antifrictional and wear proof composite materials on the basis of polyolefin's – a polyethylene of the high density (PEVP) and a polypropylene (software), in the established their optimum ratios providing functionally important physic mechanical, tribotechnical and operational properties of the composite polymeric materials working in the conditions of interaction with cotton raw. And they possess high anti-frictional properties and wear resistance in comparison with steel.

Strength and tribotechnical properties of developed anti-frictional polyethylene (APEK) and the polypropylene of compositions (APPK), anti-frictional the polypropylene of compositions (AIPPK) are given in the table.

The main strength properties of samples (the destroying stress at bend, the elasticity module at a bend of (E), impact strength and, hardness of (HB) are determined by Brinell by the standard methods - state standards. A complex of tribotechnical properties (coefficient friction  $f$ , intensity of wear) compositions at interaction with version cotton raw Tashkent-3, the 1st grade, machine collecting, humidity of 8,2% are defined on a disk tribometry.

Apparently from the table, properties the polyolefin of composite polymeric materials quite meet the functional requirements imposed to material of details of the rubbing couples of working bodies of cars and mechanisms of a cotton complex main of which the technologic and profitability of the used material are, effective decrease in damageability of cotton fiber and seeds, an exception of accumulation of static electricity, having reeled up fibers on surfaces of kolok and a spark at impact with the solid bodies which are in cotton raw.

Details of the rubbing couples of working bodies of the giving mechanism, a mobile loading crane of cotton, a telescopic tunnel formative, the tunnel car, a revolts of cotton and were made of the developed composite polymeric materials of a feeder, the plants used on procuring points and the cotton cleaning at acceptance, transportation, dismantling and supply of cotton raw in the subsequent technological installations.

To use developed composite polymeric materials as materials for details of the rubbing couples of working bodies of cotton cars and mechanisms, in the conditions of frictional a between effect of with cotton - a raw leads to increase of productivity of cars for 12-16% and a lower of power consumption for 7-18%, damages of cotton fibers and broken up of seeds, and also eliminations of possible fire of a cotton-raw and education having reeled up fibers on surfaces of composite details.

### List of literature

1. Patent of the Republic of Uzbekistan No. 05000. Anti-friction and wear-resistant polymer composition / Negmatov S.S., Gulyamov G., Shernaev A.N., Abed-Negmatova N.S., Negmatov Zh.N., Negmatova M.N., Yuldashev A.Kh., Bozorboev Sh.A., Eminov Sh.O., Tukhtasheva M.N. // Rasmiy akhborotnoma.-2015. -No. 1.
2. Ashurov N. R., Sadykov Sh. G., Abed N. S., Gulyamov G., Tukhtasheva M., Kholov Kh. N. Investigation of elastic-strength and tribotechnical properties of compositions based on high-density polyethylene. - Tashkent, 2016. - No. 3 – - p. 14-16. (02.00.00; №4)
3. Abed-Negmatova N. S., Gulyamov G., Tukhtasheva M. N. Antifriction-wear-resistant nanocomposite materials based on polyolefins // Sovremennoe sosoyanie i perspektivy razvitiya kolloidnoy khimii i nanokhimii v Uzbekistanii: Materialy Respublikanskoi nauchno-prakticheskoi konferentsii 24-25 november2014. - Tashkent, NUUZ, 2014. - p. 142-144.
4. 4 .AbedN.S., GulyamovG., NegmatovS.S., M. N. Tukhtasheva . Physico-mechanical and tribotechnical properties of composite polymeric materials of the functional purpose // Book of abstracts International Conference: "Thermophysical and mechanical properties of

- advanced materials – THERMAM 2015 and 4thRostocer international symposium: Thermophysical properties for technical thermodynamics, 17-18 September 2015. - Baku, Azerbaijan. - pp 109.
5. Abed N. S. Tukhtasheva M. N. *Primenenie kompozitsionnykh polimernykh materialov dlya kolkovykh rabochikh organov khlopopererabotyvayushchikh mashin* [Application of composite polymer materials for pegging working bodies of cotton processing machines]: Tez. dokl. Rep. of the Scientific Conference on November 6, 2015, Tashkent, 2015, pp. 169-170..
  6. Tukhtasheva M. N., Abed N. S., Khodzhiev M. T., Gulyamov G., Kalamazov R. U. *Manufacturing technology of pegged working bodies of machines and mechanisms for harvesting and storing raw cotton from composite polymer materials.* - Tashkent, 2016. - No. 3 – - p. 94-95. (02.00.00; №4)
  7. Malohat Tukhtasheva, Giyas Gulyamov, Nodira Abed, Sayibzhan Negmatov. *Technology of Receiving ant Frictional and Frictional and Wear Proof Composite Polymeric Materials and Products From Them for Cotton Cars and Mechanisms // American Scientific Journal for Engineering, Technology, and Sciences (ASRJETS) (2016) Volume 25, № 1. –pp 311-318. (02.00.00; №4)*
  8. Malohat Tukhtasheva, Giyas Gulyamov, Nodira Abed. *Details from Composite Polymeric Materials for Working Bodies of Cotton Cars and Mechanisms // Advanced Materials and Structural Engineering - Hu (Ed.). – London: Taylor & Francis Group, 2016. - pp 512-516. (05.00.00; No. 9)*
  9. Negmatov S.S., Abed N.S., Gulyamov G., Eshkobilov O.Kh. *Investigation of the influence of carbon-graphite and fibrous fillers on the antifriction properties of polyolefins, Innovative technologies, 3 (35). Karshi. pp 22-26. (2019).*
  10. Negmatov S.S., Gulyamov G., Abed N.S., Eshkobilov O.Kh., Tukhtasheva M.N. *Antifriction-wear-resistant composite polymer materials for engineering. Integrated innovative development of Zarafshan region: achievements, challenges and prospects, International scientific-practical conference, Navoiy, 27-28 november 2019y. pp 262-265.(2019).*
  11. Negmatov S.S., Gulyamov G., Ulmasov T.U., Abed N.S., Eshkobilov O.Kh., Saidova M.M., Bozorboyev Sh.A., Tukhtasheva M.N., Eminov Sh. *Investigation of the technological process of contact interaction of surfaces of metal working bodies of machines with raw cotton. Composite materials, 1. Tashkent, pp 120-124.(2020).*
  12. Tukhtasheva M.N., Negmatov S.S., Gulyamov G., Ulmasov. T.U., Abed N.S., Eshkobilov O.Kh., Saidova M.M., Eminov Sh., Bozorboyev Sh.A., Navruzov F.M. *Experimental study of the effect of fibrous fillers on antifriction, wear-resistant, technological properties of polyolefins. Composite materials, 1. Tashkent, pp 125- 128. (2020).*